



la scelta giusta  
per grandi progetti.

SCHEDA TECNICA



## RM 25

### PRIMER FOR GYPSUM SURFACES

#### PRODUCT

Highly penetrating acrylic primer to treat gypsum, scagliola and similar surfaces.

#### CHARACTERISTICS

Liquid product made from organic polymers in aqueous dispersion at high concentration and deep penetration.

#### WHERE TO USE

Preparation of the laying substrates in gypsum, scagliola and similars for the subsequent application of adhesives, smoothings and cement plasters.

#### SUBSTRATES

Gypsum surfaces, scagliola and similar.

#### CONSUMPTION

100-300 g/sqm according to the substrate.

#### PACKAGING

- 25 kg jerrycans on pallet of 675 kg;
- 5 kg jerrycans on pallet of 600 kg.
- 2 kg jerrycans on pallet of 400 kg.

#### STORAGE

It can be stored 12 months in a dry place in its original packaging.

#### ITEM SPECIFICATIONS

The surfaces in gypsum, scagliola and similars, before the application of cement based products, must be treated with a specific primers such as RM 25 by Edilcol Italia, applied by brush or roller for 100-300 g / sqm.



Cert. n. 27395-2008-AQ-ITA



Cert. n. 1982-CPR-059/471



Polizza n. 70023

## PREPARATION

- Make sure that the surfaces to be treated are clean, consistent and dry (residual humidity max 0.5%).
- Stir briefly before of the use.
- Apply the product smoothly in a single coat by brush, roller or spray.
- Wait until complete drying (4-5 h) before the application

## RECOMMENDATIONS

Do not add water to the product.  
Do not apply on non-absorbent surfaces or different from those indicated, damp substrates or substrates subject to moisture rising.  
Avoid application at temperatures below +5 ° C to +35 ° C.  
Protect from frost during storage.

Although the details contained in this product report correspond to the best of our current experience, all the above information must be confirmed after practical applications. Anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application: in every case, the user alone is fully responsible for any consequences deriving from the use of product. The values given in the technical data derived from tests conducted in laboratory , in a controlled environment, so they may be greatly modified by the conditions of installation.

## DATI TECNICI

Rev. 03 - 02/2016

Appearance:	White liquid
Composition:	polymer resins in water dispersion and selected additives
Bulk density:	≈ 1,03 g/cmc
pH:	≈ 8,0
Waiting time for heavy coatings:	4 - 5 hours
Storage:	12 months in its original packaging, protected from freezing during storage.
Contribution to smoking:	none
Hazard classification :	none (EEC 88/379)

